



NOTES

1. ROLLED CURB AND GUTTER MAY ONLY BE USED IN RESIDENTIAL SUBDIVISIONS AND ONLY WITH WRITTEN APPROVAL OF THE PUBLIC WORKS DIRECTOR.
2. FORMS SHALL BE TRUE TO LINE AND GRADE AND SECURELY STAKED.
3. THRU JOINTS SHALL BE PLACED ADJACENT TO CATCH BASINS, INLETS, CURB RETURNS, ALLEYS, OR A MAXIMUM SPACING OF 10 FEET.
4. THRU JOINTS SHALL BE 1/2" WIDE PRE-MOLDED JOINT FILLER.
5. ALL JOINTS SHALL BE CLEANED AND EDGED.
6. CONCRETE SHALL BE CEMENT CONCRETE CLASS 4000.
7. STEEL FORMS ONLY MAY BE USED ON TANGENT SECTIONS, WOOD FORMS MAY BE USED ON CURVED SECTIONS.
8. FINISH SHALL BE LIGHT BROOM.
9. THE FINISHED CONCRETE SHALL BE COVERED BY CURING COMPOUND. WATERPROOF PAPER OR PLASTIC SHEETING IN THE EVENT OF RAIN OR OTHER INCLEMENT WEATHER. CURING TIME SHALL BE AS SPECIFIED
10. ALL SIDEWALKS POURED BEHIND ROLL CURB IN RESIDENTIAL APPLICATIONS SHALL BE SIX INCHES (6") THICK OVER 2" OF CRUSHED SURFACING TOP COURSE WITH TOP OF ROCK COMPACTED TO 95% OF MAXIMUM DENSITY.

	CEMENT CONCRETE ROLLED CURB AND GUTTER		DRAWING NUMBER	STD3-7
			SCALE	NONE
			REVISION DATE	06/04
			DEPARTMENT	PW