



#### NOTES:

1. FORMS SHALL BE TRUE TO LINE AND GRADE AND SECURELY STAKED.
2. EXPANSION JOINTS SHALL BE PLACED ADJACENT TO CATCH BASINS, INLETS, CURB RETURNS, ALLEYS, OR A MAXIMUM SPACING OF 20 FEET. EXPANSION JOINTS SHALL ALSO BE PLACED BETWEEN CURB AND GUTTER AND SIDEWALK.
3. THRU JOINTS SHALL BE 3/8" WIDE PRE-MOLDED JOINT FILLER.
4. ALL JOINTS SHALL BE CLEANED AND EDGED.
5. CONCRETE SHALL HAVE A COMPRESSION STRENGTH OF 4,000 PSI.
6. STEEL FORMS ONLY MAY BE USED ON TANGENT SECTIONS, WOOD FORMS MAY BE USED ON CURVED SECTIONS.
7. FINISH SHALL BE LIGHT BROOM FINISH, PERPENDICULAR TO CURB FACE.
8. THE FINISHED CONCRETE SHALL BE COVERED BY CURING COMPOUND. WATERPROOF PAPER OR PLASTIC SHEETING IN THE EVENT OF RAIN OR OTHER INCLEMENT WEATHER. CURING TIME SHALL BE AS SPECIFIED.
9. 2" OF CRUSHED SURFACING TOP COURSE COMPACTED TO FIRM AND UNYIELDING CONDITION.
10. ALL SIDEWALKS POURED BEHIND ROLLED CURB IN RESIDENTIAL APPLICATIONS SHALL BE AN INCREASED DEPTH OF SIX INCHES (6") THICK.